

PRODUCT SPECIFICATIONS

PRODUCT NAME:	GenieMat xFIT70
DESCRIPTION:	Resilient floor system made from up to 92% recycled rubber content for shock, vibration, and noise reduction. Engineered for use where extra heavy weight drops are unavoidable in fitness, gym, sports, and training facilities, and high-traffic or acoustically-sensitive environments.
APPLICATION:	Used in facilities where overhead weight drops exceeding 100 lbs (nom. 45 kg) can occur. Typical uses of this flooring system include high-intensity interval training (HIIT), Crossfit® and Olympic-style weightlifting facilities.
FEATURES AND BENEFITS:	• Durable dual-pedestal design engineered for high impact performance in demanding fitness environments • Omni-directional interlocking system ensures secure hold and efficient installation • High-compression wear layer for superior abrasion and slip resistance and color-retention • Accessories include profiled edging, inside and outside corner pieces and accessibility compliant transitions • Will not harden or become brittle with age • Qualifies for LEED® points • Mold, bacteria, fungi, and water-resistant
COLOR:	Mostly smooth, non-porous granular rubber surface available in a variety of standard colors
DIMENSION*:	Finished Floor: 24" x 24" (nom. 610 mm x nom. 610 mm)
THICKNESS*:	Finished Floor: nom. 1-1/4" (nom. 30 mm)
WEAR LAYER DENSITY:	Shall be > 62.43 lb/ft ³ (1000 kg/m ³)
WEIGHT:	10.5 lb/ft ² (51 kg/m ²)
AREA*:	Finished Floor: 4 ft ² (0.4 m ²)
QUANTITY/PALLET*:	Varied by layer

*System is comprised of multiple layers to equal a finished elevation of 2-3/4" (nom. 70 mm). Data presented in the data sheet are for the finished floor. Underlying components will vary in thickness and dimension.

TECHNICAL DATA

RUBBER DETERIORATION/ AIR OVEN (ASTM D573):	No deterioration
COEFFICIENT OF FRICTION (ASTM D2047):	0.83 Dry, 0.88 Wet
TENSILE STRENGTH OF WEAR LAYER (ASTM D412, ISO 37):	> 300 psi (> 2.1 MPa)
ELONGATION AT BREAK (ASTM D412, ISO 37):	> 190%
TEAR RESISTANCE (ASTM D624, ISO 34):	51 lb/in (8.9 N/mm)
WEAR INDEX (ASTM D3389, ASTM C501, DIN 53516):	0.386
COMPRESSION SET (ASTM D395, ASTM D3574, ISO 1856):	4.37% Permanent Set
CRITICAL RADIANT FLUX (ASTM E648, ISO 9239):	Passes, > 697.4 BTU/hft ² (0.22 W/cm ²) / Class II
IGNITION CHARACTERISTICS (ASTM D2859):	Pass
FREEZE THAW (ASTM C666, EN 12467):	No deterioration

AROUND THE WORLD.

PLITEQ NORTH AMERICA

131 Royal Group Crescent
Vaughan, ON
L4H 1X9 Canada

4211, Yonge Street,
Suite 404, Toronto, ON M2P
2A9 Canada

2015 Main St,
Vancouver, BC
V5T 3C2 Canada

251 Little Falls Drive
Wilmington, DE
19808
United States of America
11701 N. 132nd Drive
Surprise, AZ
85379
United States of America

Calz. Gral. Mariano Escobedo
476-piso 12 Chapultepec
Morales, Anzures,
Miguel Hidalgo, 11590
Ciudad de México, CDMX
Mexico

T.+1 416 449 0049
T.+1 480 805 5560
T.+52 1 938 164 1551
info@pliteqacoustics.com
www.pliteqacoustics.com

PLITEQ UNITED KINGDOM

Office 205, Orega High
Holborn, 16 High Holborn,
London, WC1V 6BX
United Kingdom

T.+44 203 9846444
info@pliteqacoustics.com
www.pliteqacoustics.com/uk

PLITEQ MIDDLE EAST

European Business Centre
Dubai Investment Park
PO Box 473 512
United Arab Emirates

T. +971 4 567 4944
info@pliteqacoustics.com
www.pliteqacoustics.com/ae

PLITEQ ASIA PACIFIC

78 Shenton Way Tower 2,
6th Floor, Office Suite 25
079120, Singapore

T.+65 6813 2017
info@pliteqacoustics.com
www.pliteqacoustics.com/sg

PLITEQ AUSTRALIA

72 York Street, South
Melbourne, VIC, 3205
Australia

T.+61 3 9018 7696
info@pliteqacoustics.com
www.pliteqacoustics.com/au

