

GENIEBOARD® 401

NON-COMBUSTIBLE RESILIENT SUBFLOOR PANEL



PRODUCT SPECIFICATION

PRODUCT NAME:	GenieBoard® 401
DESCRIPTION:	Non-combustible panel with acoustic backing for improved impact and airborne sound control.
APPLICATION:	Can be used directly under all flooring types and on top of all GenieMat products in lightweight and heavyweight buildings.
DIMENSION:	Panel: 4' wide, 4' long (1.22 m wide, 1.22 m long)
THICKNESS:	1-1/8" (nom. 29 mm)
PANEL WEIGHT:	45 lb/panel (20.4 kg/panel)
PANEL AREA:	16 ft ² (1.48 m ²)
LEAD TIME:	4-6 weeks after receipt of order

TECHNICAL SPECIFICATION

FLEXURAL STRENGTH: (ASTM C-1185)	14.2 Mpa
SHEAR BOND STRENGTH: (ANSI 118-1 / 118-4)	345 Kpa
FALLING BALL IMPACT STRENGTH: (ASTM D-1037)	12 times
FIRE RESISTANCE: (ASTM E-119)	A1 Class/ Non Combustible
FLAMESPREAD: (ASTM E136)	No Flaming was observed
COMBUSTIBILITY PARAMETERS: (ULC-S135:2004-AM1 - R2016)	No Ignition

GENIEBOARD® 401

NON-COMBUSTIBLE RESILIENT SUBFLOOR PANEL



TECHNICAL SPECIFICATION

WATER PERMEABILITY RESISTANCE:
(CECS95:97) No significant wetness or water on back of the board

DEHALOGENATION RESISTANCE:
(JC688-2006) No Globule/ No Damp

FREEZE & THAW CYSLING:
(ASTM C-666) 14.4Mpa after 100 Cycles

MOLD AND INSECT RESISTANCE:
(ASTM D3273) Grade O; No mold developed

FLAME SPREAD INDEX
(ASTM E84) 0

SMOKE DEVELOPED INDEX
(ASTM E84) 10

CONTACT US

For Your Project Specific Questions
T. 416.449.0049 | E. info@pliteq.com

© Pliteq Inc. 2025.

®/™ Trademarks of Pliteq Inc. The information provided is accurate to the best of our knowledge at the time of issue. However, we reserve the right to make changes when necessary without further notification. Suggested application may need to be modified to conform with local building codes and conditions. We cannot accept responsibility for products that are not used, or installed, to our specifications. All listed dimensions are nominal.



www.pliteq.com

AROUND THE WORLD.

PLITEQ INC.

131 Royal Group Crescent
Vaughan, ON
L4H 1X9 Canada

4211, Yonge Street,
Suite 404, Toronto, ON M2P
2A9 Canada

2015 Main St,
Vancouver, BC
V5T 3C2 Canada

T.+1 416 449 0049
info@pliteq.com
www.pliteq.com

PLITEQ (DE)

251 Little Falls Drive
Wilmington, DE
19808
United States of America

PLITEQ (AZ)

11701 N. 132nd Drive
Surprise, AZ
85379
United States of America

T.+1 480 805 5560
info@pliteq.com
www.pliteq.com

PLITEQ MEXICO

Calz. Gral. Mariano Escobedo
476-piso 12 Chapultepec
Morales, Anzures,
Miguel Hidalgo, 11590
Ciudad de México, CDMX
Mexico

T.+52 1 938 164 1551

PLITEQ (UK) LTD.

Office 205, Orega High
Holborn, 16 High Holborn,
London, WC1V 6BX
United Kingdom

T.+44 203 9846444
info@pliteq.co.uk
www.pliteq.co.uk

PLITEQ BUILDING MATERIALS TRADING LLC.

European Business Centre
Dubai Investment Park
PO Box 473 512
United Arab Emirates

T. +971 4 567 4944
info@pliteq.ae
www.pliteq.ae

PLITEQ ASIA PACIFIC PTE LTD.

78 Shenton Way Tower 2,
6th Floor, Office Suite 25
079120, Singapore

T.+65 6813 2017
info@pliteq.sg
www.pliteq.sg

PLITEQ AUSTRALIA PTY LTD.

72 York Street, South
Melbourne, VIC, 3205
Australia

T.+61 3 9018 7696
info@pliteq.com.au
www.pliteq.com.au



© Pliteq Inc. 2026.

®™ Trademarks of Pliteq Inc. The information provided is accurate to the best of our knowledge at the time of issue. However, we reserve the right to make changes when necessary without further notification. Suggested application may need to be modified to conform with local building codes and conditions. We do not accept responsibility for products that are not used, or installed, to our specifications. All listed dimensions are nominal.